

ROXUL CURTAINROCK® 80

Insulation for Curtain Wall Systems

Product Description & Application

ROXUL CURTAINROCK® 80 is a rigid, mineral wool insulation board designed for fire rated curtain wall applications.

	Performance	Test Standard
Compliance	Mineral Fiber Block and Board Thermal Insulation - Type IVB Compliant MEA Approval, New York City Approval	ASTM C612 332-97-M
Reaction to Fire	Flame spread index = 0 ; Smoke developed index = 0 Flame spread index = 0 ; Smoke developed index = 0 Determination of Non Combustibility of Building Materials - Non Combustible Test for Non-Combustibility - Non Combustible Hot Surface Performance - 1200°F Perimeter Fire Barrier Systems - Consult UL Directory	ASTM E84 (UL 723) CAN/ULC S102 CAN/ULC S114 ASTM E136 ASTM C411 ASTM E2307/E119
Density	Nominal Density - 8.0 lbs/ft ³ (128 kgs/m ³)	ASTM C303
Dimensional Stability	Linear Shrinkage - < 1 % @ 1200°F	ASTM C356
Corrosion Resistance	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel - Passed Corrosion of Steel - Passed	ASTM C795 ASTM C665
Thermal Resistance	R-Value / inch @ 75°F 4.3 hr.ft ² .F/Btu RSI value / 25.4mm @ 24°C 0.75 m ² K/W	ASTM C518 (C177)
Reaction to Moisture	Moisture Sorption - 0.04% Determination of Fungi Resistance - Passed	ASTM C1104 ASTM C1338
Thickness Dimensions Facing	Product is available in 1" through 5" offerings (25.4mm - 127mm) 24"x48" (610mm x 1219mm) and 48"x72" (1219mm x 1829mm) Product is available with a reinforced foil facer	



Issued 12-08-16
 Supersedes 04-01-16

NOTE: *Mast Format 1995 Edition **Master Format 2004 Edition. As ROXUL Inc has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's products. ROXUL Inc's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.